



HIND INSUFOAM

PRODUCT DATA SHEET

SPRAY APPLIED POLYURATHENE FOAM SYSTEM

DESCRIPTION

Hind Insu Foam is a two component, hydro-flouro-carbon (CFC free) blown, polymeric M.D.I. based system for producing rigid urethane foam with a nominal core density of 45 kg/ cu.m. by a spray process. Grades, adjusted in reactivity, are available for both cold and hot condition.

AREAS OF APPLICATION

- Roofing & wall systems
- Tank Insulation
- Cold storages
- AirBarrierSystems

FEATURES AND BENEFITS

Hind Insu Foam system is self-flashing and provides seamless protection by sealing cracks, crevices and holes while insulating decks from temperature extremes. Hind Insu Foam provides:

- A high R-value and can reduce condensation when applied correctly.
- Enhancing energy efficiency
- Lowering lifecycle costs by reducing the operating costs.
- Improves thermal comfort.
- Stops leaks.
- Adheres well to concrete, masonry and variety of other substrate.
- Light weight.
- Dose not attract rodent and harbor mold growth.

APPLICATION

Surface Preparation

The surface of application must be thoroughly prepared by mechanical means, to remove all loose particles, laitance, etc. Oil and grease, if any, must be de-greased with suitable solvents. Any surface undulations, cracks and crevices must be duly filled or repaired with cement sand mortar mixed with SBR latex polymers such as **Hind Styrene BR**.

ENVIRONMENTAL CONSIDERATION AND SUBSTRATE TEMPERATURES

- Applicators must recognize and anticipate climatic conditions prior to application to ensure the highest quality foam and to maximize yield. Ambient air and substrate temperatures, moisture, and wind velocity are all critical determinants of foam quality and selection of the appropriate reactivity formulation.
- Variations in ambient air and substrate temperature will influence the chemical reaction of the two components, directly affecting the expansion rate, amount of rise, yield, adhesion and the resultant physical properties of the foam insulation.
- To obtain optimum results, the Hind Foam Shield system should only be spray-applied to substrates when ambient air and surface temperatures fall within the range of 10°C and 48°C.
- All substrates to be sprayed must be dry at the time of application.
- Moisture in the form of rain, fog, frost, dew, or high humidity (>85%R.H.), will react chemically with the mixed components, adversely affecting the polyurethane foam formation, dimensional stability and physical properties of the finished product.

APPLICATION EQUIPMENT

2:1 Transfer pumps are recommended for material transfer from container to the proportioner. The plural component proportioner must be capable of supplying each component within $\pm 2\%$ of the desired 1:1 mixing ratio by volume. Hose heaters should be set to deliver 50°C to 55°C materials to the spray gun. These settings will ensure thorough mixing in the spray gun mix chamber in typical applications.

- Optimum hose pressure and temperature will vary with equipment type and condition, ambient and substrate conditions, and the specific application. It is the responsibility of the applicator to properly interpret equipment technical literature, particularly information that relates to the acceptable combinations of gun chamber size, proportioner output, and material pressures.
- The relationship between proper chamber size and the capacity of the proportioner's pre-heater is critical.
- Mechanical purge spray guns (specifically direct impingement or DI type) are recommended for highest foam quality.

APPLICATION

- Polyurethane foam is sprayed onto the prepared roof surface in two components (a polyol and an isocyanate) that when mixed expand their volume to form a seamless layer of rigid foam. Within minutes this foam can be walked on and cures to 90 percent of its full strength in about four hours.
- Because polyurethane foam adheres to most surfaces, horizontal or vertical, it creates a fully-adhered, selfflashing, monolithic roof surface, with none of the critical failure points of most roof systems (seams and penetrating fasteners).
- With an insulation value of R 6.4 per inch, polyurethane foam is the most efficient form of thermal insulation variable on the market. The energy savings usually cover the cost of the roof system in a few years and by placing the insulation on the outside of the envelope, the foam reduces building expansion and contraction.

PRECAUTIONS & LIMITATIONS

- If components are below suggested temperatures, the increased viscosity of the components may cause pump cavitation resulting in unacceptable SPF application. If components are above suggested temperatures, there may be loss of blowing agent resulting in diminished yield.
- Extreme care must be taken when removing and reinstalling drum transfer pumps so as NOT to reverse the "A" and "B" components.
- Store drums at 20°C to 25°C for a minimum of 48 hours before use.
- Materials in containers should be maintained at 20°C to 25°C while in use. Material temperature should be confirmed with a thermometer or an infrared gun.
- Do not configure equipment to recirculate Hind Insu Foam components from proportioner back into drum. Do not recirculate or mix other suppliers' "A" or "B" component into Hind Insu Foam system containers

BD O DE DELLO		
PROPERTIES	VALUES	TEST METHOD
Core density(kg/m ³)	40-45	ASTM D-1622
Compressive strength (kg/cm ²)	4.2	ASTM D-1621/94
With rise		
Tensile strength, Kg/cm ²	5.1	ASTM-D 1623/78
with rise		
Thermal conductivity @ 25°C, W/M K	0.023	ASTM C-518/91
Closed cell content, apparent vol,%	96-98	ASTM D-2856
Water Vapour Transmission, perm-inch All cut surfaces	2	ASTM C-518/91
Water absorption, per cm ² (gm/cc)		ASTM C-272
Without protective coating	0.0087	
With protective coating	0.0019	
Dimentional Stability (linear Change)		ASTM D-2126
7days @ -15 °C	< 1.0	
7days @ 100 °C	2	
7days @ 70°C	2.5	
Fire resistance	Conforming to	DIN 4102
	Class - B2	
Thickness for application (in mm.)	30 (Minimum)	N.A

TECHNICAL INFORMATION

* Note: Adhesion should not be tested within one hour of application

PACKING

Pack A: 220 Kg, Pack B: 250 Kg

SHELF LIFE

- Store at room temperature in sealed drums. Moisture will react with this component to produce a surface skin of polymerized material. Protect from moisture and moisture vapour. Close all drums after use.
- Maximum permissible storage time is 12 months. The ideal storage temperature is between +20°C and +25°C.
- MDI may undergo partial crystallization at temperature below 0°C. The product can, however, be brought back into the liquid state by placing the container in a heating cabinet and carefully warming the entire contents for a short time to a maximum of 70°C.
- The Polyol Component is a low viscosity blend of polyols, hydro fluorocarbon blowing agent, catalysts and surfactant. Store at room temperature (below 25°C.) in sealed drums. Close all drums after use to prevent loss of blowing agent and absorption of moisture.

HEALTH & SAFETY PRECAUTIONS

- Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling materials used to produce foam from the **Hind Insu Foam** system. Before working with this product, you must read and become familiar with the available information on its risks, proper use and handling.
- MDI is classified as a dangerous substance and requires a hazard warning label. It must be handled with care.
- Safety goggles, impermeable protective gloves and overalls should always be worn when handling this product.
- Contaminated clothing should be removed immediately to prevent further skin contact.

Note:

- **Hindcon Chemicals** maintains a team of technically trained professionals to provide full support to your problems in construction, and recommend the correct product to suite your specific requirements. Our authorized applicators can attend your site for application of the products.
- The content of the Technical datasheet are for general information and guideline. The result shown here are generated from our laboratory or from our site experiences.
- Quality of our products are maintained as per ISO9001:2008 recommendations and continuous researches. The behavior can change as per the prevailing conditions at the time of applications.
- Since **HINDCON CHEMICALS LIMITED** has no control over the use to which the users may put the material, it does not claim or warrant that in the user's particular circumstances, the result that the user will obtain from the product will be the same as those described in this communication or that the user will find the information or recommendations complete, accurate or useful. The client must test and ascertain the safety and fitness for the product for use.
- The right to change the properties of the products is reserved with us. The proprietary rights of third parties must be observed. All orders are accepted subject to the terms of sale and delivery. Users must always refer to the most recent issue of the latest Data Sheet for the product concerned, copies of which will be supplied on request.

HINDCON CHEMICALS LIMITED

(AN ISO 9001: 2015 COMPANY)

Office: 62B, Braunfeld Row, "VASUDHA", Kolkata - 700027 Tel: 24490839. Fax: 24490849 E-mail: <u>contactus@hindcon.com</u>, hindconchemicals@yahoo.com Factory: Baniyara, Jalan Complex, Gate No.3 Howrah – 711 411 www.hindcon.com