



HIND PATCH M

PRODUCT DATA SHEET

SINGLE COMPONENT READY TO USE POLYMER MODIFIED COSMETIC MORTAR FOR REPAIRING OF CONCRETE SURFACES.

DESCRIPTION

Hind Patch M is a single component, Acrylic polymer modified cosmetic repair mortar for concrete surfaces. Its unique formulation produces Non-Shrinking mortar with no cracking when applied for a thin section < 5mm. It conforms to **EN1504**.

USES

It is used for repairing of honey comb patches of concrete surface protecting it from sulphate and chloride attack. Can be used to repair underground and marine concrete structures. It is used for smoothening of concrete surface prior to application of waterproofing polymer coatings. It is an ideal mortar for repairing of tie-rod holes used for fixing of shuttering.

ADVANTAGES

- Easy to use only water to be added and applied.
- Excellent bonding to concrete surface.
- Non-sagging properties, making it an ideal repair mortar for vertical concrete surface.
- Non -Shrink.
- High strength and waterproof.
- It high resistant to oils, sulphate and chloride attacks and freeze-thaw cycle.

APPLICATION

Substrate Preparation

The concrete surface to be properly cleaned and it should be sound and dry. It should be free of frost, curing compound membrane, waterproofing treatments, oil, laitance, other containments and dust. The area to be repaired should be free from all loose particles and properly saw-cut perpendicular to the repair surface. The surface to be pre-wetted before application of **Hind Patch M**.

Mixing

Adequate quantity of clean water **4-5 Liters** is taken in a container. **Hind Patch M** is added into the water slowly and continuously mixed with a electrical mixer (400-600rpm) fitted with a paddler for **3-4 minutes**, so that an uniform homogenous mix is obtained. The mix is allowed to rest for 2 minutes so that entrained air escapes out and finally remixed for another **30-40 seconds**. In no case more than **8 Liters** should be added to **25 Kg of Hind Patch M**.

Mixing Ratio: Mix **1 Kg Hind Patch M** with **160-165 ml** of water. (Can be adjusted as per required consistency of mortar)

Method of Application

Hind Patch M is now applied on the prepared surface with a steel trowel and that thickness of the mortar should be between 10- 40 mm. If the application of the mortar is required to be thicker than further layer is applied by the same process after initial setting of the mortar. When the mortar sets initially water is sprinkled on it and is finished with a steel/ wooden trowel. Open area applications are to be protected from rain and severe weathering conditions for the first 24 hours from the time when repairing is completed. Finally curing is to be done with wet cloth or curing compounds.

Coverage

25 Kg Bag of Hind Patch M will yield **18-20 Litres** of mortar to cover approximately 20 Sq. Mtr of area at 1 mm thickness.

PROPERTIES

Aspect	Grey Powder
Mixed Density (W/P Ratio :: 0.16 : 1)	~ 1.70 Kg/litre
Pot Life	30 minutes
Compressive Strength	> 40 N/mm ² after 7 days
	> 50 N/mm ² after 28 days
Flexural Strength	4 N/mm ² after 28 days
Bond Strength to Concrete	> 2 N/mm ² after 28 days
Thickness of application	10mm (Min.) 40mm (Max.)
Application Temperature	+5 ⁰ C to + 40 ⁰ C
Full Curing at 23 ⁰ C	28 days

Note: Higher temperature shortens the curing & working time , lower temperature extends the durations. Ideal Temperature is 23⁰ C and 50⁰ C Relative Humidity.

SHELF LIFE

Best before 12 months from the date of manufacture in unopened condition. Should be stored in a cool and dry place away from direct sunlight at temperature ranging between 2⁰ C (Min.) and 40⁰ C (Max.)

PACKING

Available in 25 Kg. HDPE Bag

HANDLING PRECAUTION

Hind Patch M is non-toxic and ingestion is to be avoided. If contact with eyes occurs, wash well immediately with water and seek medical advice.

Note:

- **Hindcon Chemicals** maintains a team of technically trained professionals to provide full support to your problems in construction, and recommend the correct product to suite your specific requirements. Our authorized applicators can attend your site for application of the products.
- The content of the Technical datasheet are for general information and guideline. The result shown here are generated from our laboratory or from our site experiences.
- Quality of our products are maintained as per ISO9001:2008 recommendations and continuous researches. The behavior can change as per the prevailing conditions at the time of applications.
- Since **HINDCON CHEMICALS LIMITED** has no control over the use to which the users may put the material, it does not claim or warrant that in the user's particular circumstances, the result that the user will obtain from the product will be the same as those described in this communication or that the user will find the information or recommendations complete, accurate or useful. The client must test and ascertain the safety and fitness for the product for use.
- The right to change the properties of the products is reserved with us. The proprietary rights of third parties must be observed. All orders are accepted subject to the terms of sale and delivery. Users must always refer to the most recent issue of the latest Data Sheet for the product concerned, copies of which will be supplied on request.

HINDCON CHEMICALS LIMITED

(AN ISO 9001: 2015 COMPANY)

Office:

62B, Braunfeld Row, "VASUDHA", Kolkata - 700027

Tel: 24490839. Fax: 24490849

E-mail: contactus@hindcon.com, hindconchemicals@yahoo.com

Factory:

Baniyara, Jalan Complex, Gate No.3

Howrah – 711 411

www.hindcon.com