



HIND PROOF NO-1

PRODUCT DATA SHEET

INTEGRAL WATERPROOFING COMPOUND FOR CEMENT MORTAR AND CONCRETE

DESCRIPTION

Hind Proof No.1 is a semi-paste, waterproofing compound which is used as an additive in cement concrete and plastering, bearing BIS Certification Mark **IS 2645:2003**.

USES

- Rendering/plastering work on all brick walls of residential structures.
- Concreting /plastering work of underground and overhead water tanks.
- For repair/maintenance work of existing damp-wall, salt petre, fungus in brick walls.
- Roof concreting work of residential & industrial structures.
- Damp proof course of residential building, basement and silos.
- Most versatile for waterproofing of structures such as tunnels, basements, culverts, water-tanks, canals, swimming pools etc

ADVANTAGES

- Total waterproofing of concrete is obtained against water pressure.
- Helps in complete crystallization of cement particles.
- Concrete is protected from weak solution of acids/chemicals.
- Eliminates/reduces dampness from plastered surface.
- Eliminates/reduces fungal growth, sweating, efflorescence, salt petre action on the plastered surface.

APPLICATION

A. Plastering

- **Hind Proof No.1** to be diluted with clean fresh water. The **proportion of mixing** is **1:12-16**, i.e. 1 part of **Hind Proof No.1**: 12 to 16 part water.
- After mixing (as stated above) the water is to be stirred uniformly and thoroughly so that the whole of **Hind Proof No.1** is dissolved in the solution.
- The solution to be added to dry mix of cement and sand mortar.
- 1 to 1.5 kg of **Hind Proof No.1** to be dissolved in 12-16 Litre of water and added for a mix of one bag(50Kg) of cement mortar and the balance water must be added separately to get the desired consistency.
- **Hind Proof No-1** is added per bag of cement depending on the mix proportion. Normally 1.5 kg per bag of cement is added for mix proportion of 1: 6 or leaner mix and 1kg per per bag of cement is added for mixed proportion of 1: 4 or richer mix.
- The quantity of **Hind Plast No.1** per bag of cement depends upon the mix proportion.

B. Concreting

- The solution to be made as mentioned in application of the product.
- Aggregate, sand and cement is added in the mixer and mixed thoroughly in dry condition and subsequently the solution is added gradually to get the desired workability. Do not add any extra water so that the W/C ratio remains unchanged from that as specified.
- 1 Kg. **Hind Proof No.1** per bag of cement to be added if cement content is 350 Kg/m³ and 1.5 Kg per bag of cement to be added for concrete with cement content less than 350 Kg/m³.

IMPORTANT

Water should not be added to make the mortar/concrete workable if it gets dried up or the use of the same is delayed.

PROPERTIES

Aspect	Semi-paste liquid.
Specific Gravity	1.06 ± 0.02
Colour	Yellow
Setting time	Normal
Chloride	0.25 %(Max)
Permeability to water as per IS: 2645	Much below the limits of the standard.

SHELF LIFE

Best before 12 months from the date of manufacture. Should be stored in a cool and dry place away from direct sunlight at temperature ranging between 2^o C (Min.) and 45^o C (Max.).

PACKING

1 Kg, 5 Kg, 25 Kg, 50 kg, 100 kg & 225 Kg Container.

HANDLING PRECAUTION

Hind Proof No.1 is non-toxic, non-flammable, Eco-friendly and ingestion is to be avoided. Any splashes to the skin must be washed with clean water. If contact with eyes occurs, wash well immediately with clean water and seek medical advice.

Note:

- **Hindcon Chemicals** maintains a team of technically trained professionals to provide full support to your problems in construction, and recommend the correct product to suite your specific requirements. Our authorized applicators can attend your site for application of the products.
- The content of the Technical datasheet are for general information and guideline. The result shown here are generated from our laboratory or from our site experiences.
- Quality of our products are maintained as per ISO9001:2008 recommendations and continuous researches. The behavior can change as per the prevailing conditions at the time of applications.
- Since **HINDCON CHEMICALS LIMITED** has no control over the use to which the users may put the material, it does not claim or warrant that in the user's particular circumstances, the result that the user will obtain from the product will be the same as those described in this communication or that the user will find the information or recommendations complete, accurate or useful. The client must test and ascertain the safety and fitness for the product for use.
- The right to change the properties of the products is reserved with us. The proprietary rights of third parties must be observed. All orders are accepted subject to the terms of sale and delivery. Users must always refer to the most recent issue of the latest Data Sheet for the product concerned, copies of which will be supplied on request.

HINDCON CHEMICALS LIMITED

Office:
62B, Braunfeld Row, "VASUDHA", Kolkata - 700027
Tel: 24490839. Fax: 24490849
E-mail: contactus@hindcon.com, hindconchemicals@yahoo.com

Factory:
Baniyara, Jalan Complex, Gate No.3
Howrah – 711 411.
www.hindcon.com